

## CLAIMS:

What is claimed is:

- 427  
212x
- 5 1. A process for preparing particles of zinc sulfide-based electroluminescent phosphor having a moisture resistant coating thereon comprising the steps of:
- 10 selecting a reaction vessel having a given height and a porous disc at the bottom thereof;
- charging said reaction vessel with phosphor particles and fluidizing said particles by introducing an inert gas into said vessel through said porous disc;
- heating said reaction vessel to a reaction temperature;
- introducing a coating precursor into said reaction vessel at a position adjacent said bottom of said vessel but above said disc;
- 15 introducing a co-reactant into said reaction vessel at a position substantially mid-way of said given height; and
- maintaining said inert gas flow, said precursor flow and said co-reactant flow for a time sufficient for a reaction to occur and coat said phosphor with said moisture resistant coating.
- 20 2. The method of Claim 1 wherein said moisture resistant coating is aluminum nitride amine.
3. The method of Claim 1 wherein said coating precursor is hexakis(dimethylamido)dialuminum.
- 25 4. The method of Claim 3 wherein said co-reactant is anhydrous ammonia.
5. The method of Claim 4 wherein said reaction temperature is about 150 to 225°C.

6. An apparatus for manufacturing commercial quantities of zinc sulfide-based electroluminescent phosphor having a moisture resistant coating thereon, said apparatus comprising:

- 118
- 5 a reaction vessel having a given height and a porous disc at the bottom thereof;  
a supply of phosphor particles within said vessel;  
a first supply of an inert gas for fluidizing said particles, said first supply of inert gas entering said vessel through said porous disc;  
a heater surrounding said reaction vessel for heating said reaction vessel to a reaction temperature;
- 10 a supply of a coating precursor;  
first means for conducting said coating precursor from said supply to said reaction vessel, said first means entering said reaction vessel at said bottom of said vessel at a position above said porous disc;  
a supply of a co-reactant; and
- 15 a second means for conducting said co-reactant from said supply to said reaction vessel, said second means entering said reaction vessel at a position substantially mid-way of said given height.

7. The apparatus of Claim 6 wherein said reaction vessel has a diameter of about 10 inches.

8. The apparatus of Claim 7 wherein said reaction vessel is stainless steel.